

250 Chester Street

Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT A902 SUPPORT: FLOCK SUBSTRATE: ABS

CERT NO.: 231128 - 1214

## FORD WSS-M15P4-I

OEM Rev Date: Jul 21

Assembly Performance, Hard Mold-in-Color Interior Components

Horizontal or Vertical Parts At or Above the Belt Line

Above the Belt



٦	ΓΔΡ	F	R	FO	H	REN	ΛFN	JTS:

TAPE REQUIREMENTS: SECTION: 3.6 Impact Resistance 23°C Room Temperature Impact @ 610 mm	Specification  No Cracking, Breaking or Separation	Results Stable, No Cracks, Breaks or Lifting	<u>Status</u> Pass
SECTION: <b>3.10 Fogging, Method A - Photometric</b> 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT	Specification 70 Units	SAE J1756 <b>Results</b> 77.9	<u>Status</u> Pass
SECTION: 3.11 Odor Odor, Condition 1 - 24 hrs @ RT, Deionized Water	Specification 3 Max Rating	FLTM BO 131-03 Results Not Tested	<u>Status</u> Not Tested
Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water	3 Max Rating	Not Tested	Not Tested
Odor, Condition 3 - 2 hrs @ 65°C	3 Max Rating	Not Tested	Not Tested
SECTION: 3.12 Flammability Initial, Component,	Specification < 100 mm / min	ISO 3795 <u><b>Results</b></u> < B 75	Status Pass
SECTION: <b>3.14 Determination of 90 Degree Adhesion Strength</b> 3.14.1 Initial Adhesive Strength	Specification 0.48 N / mm	FLTM BO 131-03 <u><b>Results</b></u> 0.91	Status Pass
3.14.2 Long Term Heat Exposure - 7 Days @ 100°C	75% of Original Value	1.04	Pass
3.14.3 Short Term Heat, Humidity and Cold Exposure	75% of Original Value	0.99	Pass
SECTION: <b>3.14 Determination of 90 Degree Adhesion Strength</b> 3.14.1 Initial Adhesive Strength	Specification	FLTM BO 131-03 <b>Results</b> No Lifting or Appearnce Changes	Status Pass
3.14.2 Long Term Heat Exposure - 7 Days @ 100°C		No Lifting or Appearnce Changes	Pass
3.14.3 Short Term Heat, Humidity and Cold Exposure			_

**CERTIFIED BY:** 



5 hrs @ -30°C

5 hrs @ 100°C

5 hrs @ -30°C

5 hrs @ 100°C

30 mins @ 23°C / 50% RH

30 mins @ 23°C / 50% RH

2 hrs @ 50°C / 95% RH

30 mins @ 23°C / 50% RH

30 mins @ 23°C / 50% RH

ISSUE DATE: 1-1-25

No Lifting or Appearnce Changes

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

**Pass** 

**Pass** 

**Pass** 

**Pass** 

**Pass** 

**Pass** 

**Pass** 

**Pass** 

**Pass**