



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT A902 PET
SUPPORT: FLOCK
SUBSTRATE: ABS
CERT NO.: 231128 - 1214



FORD WSS-M15P4-I
OEM Rev Date: Jul 21
Assembly Performance, Hard Mold-in-Color Interior Components
Horizontal or Vertical Parts At or Above the Belt Line
Above the Belt

TAPE REQUIREMENTS:

SECTION: **3.6 Impact Resistance**
23°C Room Temperature Impact @ 610 mm

Specification	Results	Status
No Cracking, Breaking or Separation	Stable, No Cracks, Breaks or Lifting	Pass

SECTION: **3.10 Fogging, Method A - Photometric**
3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification	Reference	Results	Status
70 Units	SAE J1756	85.7	Pass

SECTION: **3.11 Odor**
Odor, Condition 1 - 24 hrs @ RT, Deionized Water

Specification	Reference	Results	Status
3 Max Rating	FLTM BO 131-03	Not Tested	Not Tested

Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

3 Max Rating		Not Tested	Not Tested
--------------	--	------------	------------

Odor, Condition 3 - 2 hrs @ 65°C

3 Max Rating		Not Tested	Not Tested
--------------	--	------------	------------

SECTION: **3.12 Flammability**
Initial, Component,

Specification	Reference	Results	Status
< 100 mm / min	ISO 3795	SE	Pass

SECTION: **3.14 Determination of 90 Degree Adhesion Strength**
3.14.1 Initial Adhesive Strength

Specification	Reference	Results	Status
0.48 N / mm	FLTM BO 131-03	0.76	Pass

3.14.2 Long Term Heat Exposure - 7 Days @ 100°C

75% of Original Value		1.42	Pass
-----------------------	--	------	------

3.14.3 Short Term Heat, Humidity and Cold Exposure

75% of Original Value		1.12	Pass
-----------------------	--	------	------

SECTION: **3.14 Determination of 90 Degree Adhesion Strength**
3.14.1 Initial Adhesive Strength

Specification	Reference	Results	Status
	FLTM BO 131-03	No Lifting or Appearance Changes	Pass


3.14.2 Long Term Heat Exposure - 7 Days @ 100°C

		No Lifting or Appearance Changes	Pass
--	--	----------------------------------	------

3.14.3 Short Term Heat, Humidity and Cold Exposure
5 hrs @ -30°C
30 mins @ 23°C / 50% RH
5 hrs @ 100°C
30 mins @ 23°C / 50% RH
2 hrs @ 50°C / 95% RH
30 mins @ 23°C / 50% RH
5 hrs @ -30°C
30 mins @ 23°C / 50% RH
5 hrs @ 100°C

		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass
		No Lifting or Appearance Changes	Pass

CERTIFIED BY:



ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.