



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 0900X PET**
 SUPPORT: **FLOCK**
 SUBSTRATE: **SS**
 STD CERT NO.: **231204 - 0816**



GM 9985281
 OEM Rev Date: Sep 15
 Adhesive, Film
 Table 1: Material Properties as Received
 Low Temperature

Table 1: Material Properties as Received

3 Requirements

SECTION: **Mass**

Product Less Liner

<u>Specification</u>	<u>Results</u>	<u>Status</u>
> 0.06 < 0.20 kg/m²	0.07	Pass

SECTION: **Solids Content**

Solids, 45 mins @ 105°C

<u>Specification</u>	<u>Results</u>	<u>Status</u>
94.5 % min	99.6	Pass

SECTION: **Thickness of Adhesive**

0.09 to 1.75 mm (.004 to .065 in)

TAPPI 411

<u>Specification</u>	<u>Results</u>	<u>Status</u>
> 0.090 < 1.650 mm	0.104	Pass

SECTION: **Peel Adhesion**

Table 1, Initial, Room Temp

ASTM D3330

<u>Specification</u>	<u>Results</u>	<u>Status</u>
535 N / m	538.6	Pass

SECTION: **Holding Power**

Table 1, Low Temp, 1000g @ 23°C, PET Support

ASTM D3564 Method A

<u>Specification</u>	<u>Results</u>	<u>Status</u>
> 25 mins	95.0	Pass

SECTION: **Liner Removal**

Table 1, Initial, Room Temp

ASTM D3330

<u>Specification</u>	<u>Results</u>	<u>Status</u>
< 45 N / m	6.7	Pass

CERTIFIED BY:



Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.