



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

email: psa.tape@averydennison.com URL:

tapes.averydennison.com

PRODUCT: FT 8327

SUPPORT: SHODDY PAD

SUBSTRATE:

CERT NO .: 221214 - 0850

GM 9985281

OEM Rev Date: Aug 03

ASTM D3330

Performance Requirements for Adhesive, Film Table 1: Material Properties as Received Table 2: Material Properties 90 Day Aged

High Temperature



Status

Results

TAPE REQUIREMENTS:

SECTION: Peel Adhesion

3 Requirements

Table 1, Initial, 15 mins @ RT	535 N/m	938.7	Pass
Table 2, 90 Day Aged @ 35°C, PET Support	420 N/m	1,370	Pass

Specification

SECTION: Holding Power	ASTM D3654	Specification	<u>Results</u>	<u>Status</u>
Table 1, High Temp, 1000g @ 23°C, PET Support		> 3000 minutes	> 4,500	Pass
Table 2, 90 Day Aged @ 35°C, 1000g @ 23°C, PE	Γ Support	> 3000 minutes	> 3,500	Pass

Passing high temperature requirements passes low temperature 25 minute holding power as well

SECTION: Liner Removal Table 1, Initial, Room Temp	ASTM D3330	Specification < 45 N/m	Results 16.9	<u>Status</u> Pass
Table 2, 90 Day Aged @ 35°C		< 45 N/m	18.1	Pass

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.