



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT B EZ
SUPPORT: SHODDY PAD
SUBSTRATE: PAINTED METAL
CERT NO.: 221214 - 0847



GM 9985281
OEM Rev Date: Aug 03
Performance Requirements for Adhesive, Film
Table 1: Material Properties as Received
Table 2: Material Properties 90 Day Aged
High Temperature

TAPE REQUIREMENTS:

3 Requirements

SECTION: Peel Adhesion ASTM D3330 Specification Results Status
535 N / m 582.6 Pass

Table 2, 90 Day Aged @ 35°C, PET Support 420 N / m 1,332 Pass

SECTION: Holding Power ASTM D3654 Specification Results Status
> 3000 minutes > 4,500 Pass

Table 2, 90 Day Aged @ 35°C, 1000g @ 23°C, PET Support > 3000 minutes > 3,500 Pass

Passing high temperature requirements passes low temperature 25 minute holding power as well

SECTION: Liner Removal ASTM D3330 Specification Results Status
< 45 N / m 15.2 Pass

Table 2, 90 Day Aged @ 35°C < 45 N / m 17.5 Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.