

888-358-4469

**GENERAL REQUIREMENTS:** 

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax: email:

URL:

Painesville, Ohio 44077

## **TEST REPORT**

SUBSTRATE: ABS

FT 8392 PET FOAM 221214 - 0846



**GMCH MSP 200062** OEM Rev Date: Oct 17

PRODUCT:

SUPPORT:

CERT NO .:

Pressure Sensitive Adhesives - Permanent Bond Double Coated Tape - With Polyester Carrier Permanent Bond

| SECTION: 3.1.3 Service Temperature Test             |                                    |                                      |               |
|---|------------------------------------|--------------------------------------|---------------|
| Condition   | Specification                      | Results                              | <u>Status</u> |
| 3.1.3.3 Permanent Bond: 96 hrs @ -40°C              | No Adhesion Loss or Separation     | Good, Stable, No Lifting             | Pass          |
| 3.1.3.3 Permanent Bond: 96 hrs @ 93°C               | No Adhesion Loss or Separation     | Good, Stable, No Lifting             | Pass          |
| SECTION: 3.1.3 Service Temperature Test             |                                    |                                      |               |
| Condition   | Specification                      | Results                              | <u>Status</u> |
| 3.1.3.3 Permanent Bond: 96 hrs @ -40°C              | 2 lb                               | 7.03                                 | Pass          |
| 3.1.3.3 Permanent Bond: 96 hrs @ 93°C               | 2 lb                               | 13.80                                | Pass          |
| SECTION: 3.1.4 Humidity                             |                                    |                                      |               |
| Condition   | Specification                      | <u>Results</u>                       | <u>Status</u> |
| 3.1.4 50 hrs @ 38°C / 95% RH                        | No Adhesion Loss, Discoloration or | Stable, No Lifting or Visible Change | Pass          |
| CECTION 245 Objectionship Oder                      | Softening                          |                                      |               |
| SECTION: 3.1.5 Objectionable Odor<br>Condition      | Specification                      | Posulte                              | Status        |
| 3.1.5 1 hr @ 93°C                                   | 2 or Less Rating                   | <u>Results</u><br>1.3                | Pass          |
|   |                                    |                                      | 1 435         |
| 3.1.5 1 hr @ 93°C, 1 hr @ RT                        | 2 or Less Rating                   | 1.0                                  | Pass          |
| SECTION: 3.1.7 Creep                                |                                    |                                      |               |
| Condition   | Specification                      | <u>Results</u>                       | <u>Status</u> |
| 3.1.7 3.5 hrs @ 23°C under 1 lb load                | No Slip                            | No Slip                              | Pass          |
| GENERAL REQUIREMENTS:                               |                                    |                                      |               |
| SECTION: 3.1.3 Service Temperature Test             |                                    | ASTM D903 / D3330                    |               |
| Condition   | Specification                      | Results                              | Status        |
| 4.1.1.1 a) As Bonded                                | 3.4 lb                             | 6.29                                 | Pass          |
|   |                                    | 11.10                                | _             |
| 4.1.1.1 b) 72 hrs @ 93°C                            | 2 lb                               | 14.49                                | Pass          |
| 4.1.1.1 c) 24 hrs @ -40⁰C                           | 2 lb                               | 7.64                                 | Pass          |
| , 0   |                                    |                                      |               |
| 4.1.1.1 d) 48 hrs @ 38ºC / 100% RH                  | 2 lb                               | 7.80                                 | Pass          |
| 4.1.1.1 e) 800 hrs @ 93⁰C                           | 2 lb                               | 4.01                                 | Pass          |
|   | 2 15                               | 4.01                                 | 1 435         |
| SECTION: 4.1.1.2 Static Shear                       |                                    |                                      |               |
| Condition   | <b>Specification</b>               | Results                              | <u>Status</u> |
| 4.1.1.2 Ambient, 6 hrs @ 23°C under 2.5 kg Load     | No Slip                            | No Slip                              | Pass          |
| SECTION: 4.1.1.3 Suggested Adhesive Requirements fo | r Handling During Assembly         | ASTM D882                            |               |
| <u>Condition</u>                                    | Specification                      | Results                              | Status        |
| 4.1.1.3 a) Tensile (Breaking Factor)                | 10 lbf                             | 10.1                                 | Pass          |
| · · · · · · · · · · · · · · · · · · ·               |                                    |                                      |               |
| 4.1.1.3 b) Elongation                               | <b>60</b> %                        | 42.8                                 | Pass          |
|   |                                    |                                      |               |
| 1 001   |                                    |                                      |               |

Jake Cowdrick, Automotive Application Specialist

**ISSUE DATE:** 

1-1-25

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: 5-9-2018

CERTIFIED BY: