



250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

psa.tape@averydennison.com email: URL: tapes.averydennison.com

**GENERAL REQUIREMENTS:** 

PRODUCT: FT 8392 **PEU FOAM** SUPPORT: SUBSTRATE: **ABS** 

221214 - 0846 CERT NO .:

**GMCH MSP 200062** OEM Rev Date: Oct 17

Pressure Sensitive Adhesives - Permanent Bond Double Coated Tape - With Polyester Carrier

Permanent Bond

SECTION: <b>3.1.3 Service Temperature Test</b> Condition  3.1.3.3 Permanent Bond: 96 hrs @ -40°C	Specification No Adhesion Loss or Separation	Results Good, Stable, No Lifting	Status Pass
3.1.3.3 Permanent Bond: 96 hrs @ 93°C	No Adhesion Loss or Separation	Good, Stable, No Lifting	Pass
SECTION: 3.1.3 Service Temperature Test Condition 3.1.3.3 Permanent Bond: 96 hrs @ -40°C	Specification 2 lb	Results 7.07	Status Pass
3.1.3.3 Permanent Bond: 96 hrs @ 93°C	2 lb	9.57	Pass
SECTION: <b>3.1.4 Humidity</b> Condition 3.1.4 50 hrs @ 38°C / 95% RH	Specification  No Adhesion Loss, Discoloration or Softening	<u>Results</u> Stable, No Lifting or Visible Change	Status Pass
SECTION: 3.1.5 Objectionable Odor Condition 3.1.5 1 hr @ 93°C	Specification 2 or Less Rating	Results 1.3	Status Pass
3.1.5 1 hr @ 93°C, 1 hr @ RT	2 or Less Rating	1.0	Pass
SECTION: 3.1.7 Creep Condition 3.1.7 3.5 hrs @ 23°C under 1 lb load	Specification No Slip	<u>Results</u> No Slip	Status Pass
GENERAL REQUIREMENTS: SECTION: 3.1.3 Service Temperature Test Condition 4.1.1.1 a) As Bonded	Specification  3.4 lb	NSTM D903 / D3330  Results  6.25	Status Pass
4.1.1.1 b) 72 hrs @ 93°C	2 lb	11.63	Pass
4.1.1.1 c) 24 hrs @ -40°C	2 lb	7.87	Pass
4.1.1.1 d) 48 hrs @ 38°C / 100% RH	2 lb	7.83	Pass
4.1.1.1 e) 800 hrs @ 93°C	2 lb	3.42	Pass
SECTION: 4.1.1.2 Static Shear Condition 4.1.1.2 Ambient, 6 hrs @ 23°C under 2.5 kg Load	Specification  No Slip	Results No Slip	Status Pass
SECTION: 4.1.1.3 Suggested Adhesive Requirements  Condition	for Handling During Assembly Specification	NSTM D882  Results	Status

**CERTIFIED BY:** 

4.1.1.3 b) Elongation

4.1.1.3 a) Tensile (Breaking Factor)

ISSUE DATE: 1-1-25

5-9-2018

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

10 lbf

60 %

Jake Cowdrick, Automotive Application Specialist

10.1

42.8

**Pass** 

Pass

ACCREDITED

TESTING LABORATORY