



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

SAMPLE: FT 0900X
SUPPORT: FLOCK
SUBSTRATE: TPO
CERT NO.: 241001 - 0532

GMW 14444-CODE-2
OEM Rev Date: Jan-04
Material Related Interior Part Performance
CODE 2 Position Within Vehicle is Exposed to Direct Sunlight at Lower Temperatures
C - All Parts In Contact With Customer Feet, e.g. Floor Mat, Door Trim
Mechanically

TAPE REQUIREMENTS:

SECTION: 4.3 Flammability
Initial, Component
GMW3232
Specification < 100 mm / min
Results < B 25
Status Pass

SECTION: 4.4.6 Scratch Resistance\*
100 Cycles CS-10, 500 g Load
Specification No Wear Thru to Fabric Backing
Results Not Tested
Status Not Tested

SECTION: 4.5.1 Odor\*
Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water
GMW 3205
Specification > 4 Rating
Results Not Tested
Status Not Tested

Dry Condition, Coding B - 24 hrs @ 70°C
> 4 Rating
Not Tested
Not Tested

High Temp Condition - 24 hrs @ 105°C
> 4 Rating
Not Tested
Not Tested

SECTION: 4.5.1 Emission Testing
Fogging, 3 hrs @ 100°C, 21°C Cooling, Post 60 mins @ RT
GMW 3235
Specification > 60 %
Results 48.3
Status Fail

SECTION: 4.5.2 Impact Resistance
At Temperature, 23°C
GMW 14093 CODE 3, Apparatus A
Specification
Results No Separation or Cracks
Status Pass
No Breakage, Cracks or Separation from 2 - 2.5 J Impacts

4.5.6 Adhesive Requirements of Pressure Sensitive Adhesive, Mechanically Retained Bonded Items

TEST: Adhesion
As Received
GMW 14892
Specification 350 N / m
Results 639.1
Mode ADHESIVE
Status Pass

Humidity - GMW 14729 Option A, 144 hrs @ 38°C / 100% RH
350 N / m
468.7
ADHESIVE
Pass

Oven Aged, 24 hrs @ 95°C, < 60s
350 N / m
483.3
ADHESIVE
Pass

Environmental Cycles 2(x), GMW 14124 Cycle M
350 N / m
553.9
ADHESIVE
Pass

CERTIFIED BY: [Signature]
David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.