## **TEST REPORT**

FT 3043



250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

**TAPE REQUIREMENTS:** 

Initial, Component

**SECTION: 4.3 Flammability** 

psa.tape@averydennison.com email: URL: tapes.averydennison.com

SUPPORT: **FLOCK** SUBSTRATE: TPO CERT NO .:

221214 - 0903

## GMW 14444-CODE-3

OEM Rev Date: 0

SAMPLE:

Material Related Interior Part Performance

CODE 3 Position Within Vehicle is Not Exposed to Direct Sunlight C - All Parts In Contact With Customer Feet, e.g. Floor Mat, Door Trim

Mechanically

GMW3232

**Specification** < 100 mm / min Results < B 25

**Status** Pass

ACCREDITED

TESTING LABORATORY

SECTION: 4.4.6 Scratch Resistance

100 Cycles CS-10, 500 g Load

**Specification** 

No Wear Thru to Fabric Backing

Results Good, No Wear Thru **Status Pass** 

SECTION: 4.5.1 Odor

GMW 3205 Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water

**Specification** > 4 Rating

Results 9 Just Noticeable **Status Pass** 

Dry Condition, Coding B - 24 hrs @ 70°C

> 4 Rating

9 Just Noticeable

**Pass** 

High Temp Condition - 24 hrs @ 105°C

> 4 Rating

8 Noticeable, Trace

**Pass** 

SECTION: 4.5.1 Emission Testing

GMW 3235 Fogging, 3 hrs @ 100°C, 21°C Cooling, Post 60 mins @ RT

Specification > 60 %

Results 100.0

**Status Pass** 

SECTION: 4.5.2 Impact Resistance

After 4 hrs @ -30°C

GMW 14093 CODE 3, Apparatus A

**Specification** 

Results No Separation or Cracks Status **Pass** 

No Breakage, Cracks or Separation from 2 - 2.5 J Impacts

4.5.6 Adhesive Requirements of Pressure Sensitive Adhesive, Mechanically Retained Bonded Items

TEST: GMW 14892 **Specification Adhesion** Results **Mode Status** 350 N/m 727.2 ADHESIVE As Received **Pass** 350 N/m 989.9 ADHESIVE Humidity - GMW 14729 Option A, 144 hrs @ 38°C / 100% RH **Pass** 350 N/m 589.5 **ADHESIVE** Oven Aged, 24 hrs @ 85°C, < 60s **Pass** 

Environmental Cycles 2(x), GMW 14124 Cycle M

350 N/m

11808

COHESIVE

Cohesive-Pass

**CERTIFIED BY:** 

wdrick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.