Δ			TEST REPORT			
AVERY DENNISONSAMPLE: SUPPORT:250 Chester StreetSUBSTRATE: CERT NO.:		FT 8327 12 PT BD EPDM FOAM PP 221214 - 0903				
Phone: Fax: email: URL:	iei, Onio 44077 CERTINOL: 221214 - 0903 866-GO-AVERY (866-462-8379) GMW 14444-CODE-3 9sa.tape@averydennison.com OEM Rev Date: 0 tapes.averydennison.com Material Related Interior Part Performance CODE 3 Position Within Vehicle is Not Exposed to Direct Sunlight C - All Parts In Contact With Customer Feet, e.g. Floor Mat, Door Trim Mechanically Mechanically					
TAPE REQUIREMENTS: SECTION: 4.3 Flammability GMW3232 Initial, Component GMW3232		Specification < 100 mm / min		<mark>Results</mark> ≤ B 25		
SECTION: 4.4.6 Scratch Resistance 100 Cycles CS-10, 500 g Load No		Specification No Wear Thru to Fabric Backing	Results Not Applicable		<u>Status</u> Not Applicable	
SECTION: 4.5.1 Odor GMW 3205 Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water			Specification >4 Rating		Results 8 Noticeable, Trace	
Dry Condit	tion, Coding B - 24 hrs @ 70ºC		> 4 Rating	7 Clearly Noticeable,	But Not Objectionable	Pass
High Temp Condition - 24 hrs @ 105°C			> 4 Rating	7 Clearly Noticeable,	y Noticeable, But Not Objectionable	
SECTION: 4.5.1 Emission Testing GMW 3235 Fogging, 3 hrs @ 100°C, 21°C Cooling, Post 60 mins @ RT			Specification > 60 %	Results 94.8		<u>Status</u> Pass
			Dis A <u>Specification</u> Discrete Breakage, Cracks or Separation from 2 - 2.5 J Impacts	<u>Results</u> No Separation or Cracks		<u>Status</u> Pass
4.5.6 Adl TEST: As Receive	hesive Requirements of Pressure S Adhesion ed	GMW 14892	ve, Mechanically Retained Bond <u>Specification</u> 350 N / m	ed Items <u>Results</u> 776.3	Mode ADHESIVE	<u>Status</u> Pass
Humidity -	GMW 14729 Option A, 144 hrs @ 386	°C / 100% RH	350 N/m	787.4	ADHESIVE	Pass
Oven Aged, 24 hrs @ 85ºC, < 60s		350 N/m	434.2	ADHESIVE	Pass	
Environmental Cycles 2(x), GMW 14124 Cycle M			350 N / m	953.1	ADHESIVE	Pass
CERTIFIED BY:					<u>1-25</u>	
	materials tested to OEM requiremen	us @ / 2°F +/- 2°F and	1 50% RH +/- 5%. Test uncertainty and mir	ior exclusions are available	omine or upon request.	

aterials tested to OEM requirements @ 72°F +1-2°F and 50% RH +7-5%. Lest uncertainty and minor exclusions are available online or upon reque This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.