



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

SAMPLE: FT 8327 12 PT BD
SUPPORT: XLPE FOAM
SUBSTRATE: SS
CERT NO.: 221214 - 0903



GMW 14444-CODE-3
OEM Rev Date: 0

Material Related Interior Part Performance
CODE 3 Position Within Vehicle is Not Exposed to Direct Sunlight
C - All Parts In Contact With Customer Feet, e.g. Floor Mat, Door Trim
Mechanically

TAPE REQUIREMENTS:

SECTION: **4.3 Flammability**
Initial, Component

GMW3232

Specification
< 100 mm / min

Results
< B 25

Status
Pass

SECTION: **4.4.6 Scratch Resistance**
100 Cycles CS-10, 500 g Load

Specification
No Wear Thru to Fabric Backing

Results
Not Applicable

Status
Not Applicable

SECTION: **4.5.1 Odor** GMW 3205
Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water

Specification
> 4 Rating

Results
7 Clearly Noticeable, But Not Objectionable

Status
Pass

Dry Condition, Coding B - 24 hrs @ 70°C

> 4 Rating

6 Tolerable

Pass

High Temp Condition - 24 hrs @ 105°C

> 4 Rating

7 Clearly Noticeable, But Not Objectionable

Pass

SECTION: **4.5.1 Emission Testing** GMW 3235
Fogging, 3 hrs @ 100°C, 21°C Cooling, Post 60 mins @ RT

Specification
> 60 %

Results
75.5

Status
Pass

SECTION: **4.5.2 Impact Resistance** GMW 14093 CODE 3, Apparatus A
After 4 hrs @ -30°C

Specification
**No Breakage, Cracks or Separation
from 2 - 2.5 J Impacts**

Results
No Separation or Cracks

Status
Pass

4.5.6 Adhesive Requirements of Pressure Sensitive Adhesive, Mechanically Retained Bonded Items

TEST: **Adhesion** GMW 14892
As Received

Specification
350 N / m

Results
831.1

Mode
ADHESIVE

Status
Pass

Humidity - GMW 14729 Option A, 144 hrs @ 38°C / 100% RH

350 N / m

660.1

ADHESIVE

Pass

Oven Aged, 24 hrs @ 85°C, < 60s

350 N / m

415.6

ADHESIVE

Pass

Environmental Cycles 2(x), GMW 14124 Cycle M

350 N / m

1096.1

ADHESIVE

Pass

CERTIFIED BY:


Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.