



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

SAMPLE: FT 8327
SUPPORT: EPDM FOAM
SUBSTRATE: PP
CERT NO.: 221214 - 0903



GMW 14444-CODE-3

OEM Rev Date: 0
Material Related Interior Part Performance
CODE 3 Position Within Vehicle is Not Exposed to Direct Sunlight
C - All Parts In Contact With Customer Feet, e.g. Floor Mat, Door Trim
Mechanically

TAPE REQUIREMENTS:

SECTION: **4.3 Flammability**
Initial, Component

GMW3232	<u>Specification</u> < 100 mm / min	<u>Results</u> < B 25	<u>Status</u> Pass
---------	--	--------------------------	------------------------------

SECTION: **4.4.6 Scratch Resistance**
100 Cycles CS-10, 500 g Load

	<u>Specification</u> No Wear Thru to Fabric Backing	<u>Results</u> Not Applicable	<u>Status</u> Not Applicable
--	---	----------------------------------	---------------------------------

SECTION: **4.5.1 Odor** GMW 3205
Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water

	<u>Specification</u> > 4 Rating	<u>Results</u> 8 Noticeable, Trace	<u>Status</u> Pass
--	--	---------------------------------------	------------------------------

Dry Condition, Coding B - 24 hrs @ 70°C

	> 4 Rating	7 Clearly Noticeable, But Not Objectionable	Pass
--	----------------------	---	-------------

High Temp Condition - 24 hrs @ 105°C

	> 4 Rating	7 Clearly Noticeable, But Not Objectionable	Pass
--	----------------------	---	-------------

SECTION: **4.5.1 Emission Testing** GMW 3235
Fogging, 3 hrs @ 100°C, 21°C Cooling, Post 60 mins @ RT

	<u>Specification</u> > 60 %	<u>Results</u> 94.8	<u>Status</u> Pass
--	--	------------------------	------------------------------

SECTION: **4.5.2 Impact Resistance** GMW 14093 CODE 3, Apparatus A
After 4 hrs @ -30°C

	<u>Specification</u> No Breakage, Cracks or Separation from 2 - 2.5 J Impacts	<u>Results</u> No Separation or Cracks	<u>Status</u> Pass
--	---	---	------------------------------

4.5.6 Adhesive Requirements of Pressure Sensitive Adhesive, Mechanically Retained Bonded Items

TEST: **Adhesion** GMW 14892
As Received

	<u>Specification</u> 350 N / m	<u>Results</u> 776.3	<u>Mode</u> ADHESIVE	<u>Status</u> Pass
--	--	-------------------------	-------------------------	------------------------------

Humidity - GMW 14729 Option A, 144 hrs @ 38°C / 100% RH

	350 N / m	787.4	ADHESIVE	Pass
--	------------------	-------	----------	-------------


Oven Aged, 24 hrs @ 85°C, < 60s

	350 N / m	434.2	ADHESIVE	Pass
--	------------------	-------	----------	-------------

Environmental Cycles 2(x), GMW 14124 Cycle M

	350 N / m	953.1	ADHESIVE	Pass
--	------------------	-------	----------	-------------

CERTIFIED BY:



Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.