



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 1126**  
 SUPPORT: **EPDM FOAM**  
 SUBSTRATE: **PP**  
 STD CERT NO.: **240124 - 0655**



**GMW 16443 -TYPE I**

OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Foam  
 Type I - An adhesive backed foam composite that is entrapped  
 and/or mechanically retained for the life of the vehicle  
 GMW 3221 Code A - 50% RH (+/- 5%)

**TAPE REQUIREMENTS:**

**3.5.1 Type I Exposure**

**SECTION 3.3 Edge Adhesion**

3.3, Initial, As Received

<u>Specification</u>	<u>Results</u>	<u>Status</u>
<b>Securely Bonded</b>	Stable, No Lifting or Removal	<b>Pass</b>

3.5.4, Heat Aged, ISO 188, 168 hrs @ 80C

<b>Securely Bonded</b>	Stable, No Lifting or Removal	<b>Pass</b>
------------------------	-------------------------------	-------------

3.5.5, Humidity, GMW 14729 Option A, 168 hrs @ 38°C / 100% RH

<b>Securely Bonded</b>	Stable, No Lifting or Removal	<b>Pass</b>
------------------------	-------------------------------	-------------

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Specialty Tape Division.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.