



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 1126**
SUPPORT: **PE FOAM**
SUBSTRATE: **ABS**
STD CERT NO.: **240124 - 0730**



GMW 16443 -TYPE I

OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Foam
Type I - An adhesive backed foam composite that is entrapped
and/or mechanically retained for the life of the vehicle
GMW 3221 Code A - 50% RH (+/- 5%)

TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION 3.3 Edge Adhesion

3.3, Initial, As Received

<u>Specification</u>	<u>Results</u>	<u>Status</u>
Securely Bonded	Stable, No Lifting or Removal	Pass

3.5.4, Heat Aged, ISO 188, 168 hrs @ 80C

Securely Bonded	Stable, No Lifting or Removal	Pass
------------------------	-------------------------------	-------------

3.5.5, Humidity, GMW 14729 Option A, 168 hrs @ 38°C / 100% RH

Securely Bonded	Stable, No Lifting or Removal	Pass
------------------------	-------------------------------	-------------

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Specialty Tape Division.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.