

250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

 PRODUCT:
 FT 1903

 SUPPORT:
 2 MIL PET

 SUBSTRATE:
 PP

 CERT NO.:
 250217 - 0810



GMW 16443-TYPE-I

OEM Rev Date: Aug 18 Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

TAPE REQUIREMENTS:				
3.5.1 Type I Exposure				
SECTION 3.3.3 Edge Adhesion				
3.5.3, Initial, As Received - 24 hrs @ RT				

Specification Securely Bonded Results Stable, No Lifting or Removal

Stable, No Lifting or Removal

Status Pass

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188,

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option

Securely Bonded

Securely Bonded

Stable, No Lifting or Removal

Pass

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 2-17-2025 Page 1 of 1

Pass

	PRODUCT:	FT 1903
Appendix A Table A1	SUPPORT:	2 MIL PET
	SUBSTRATE:	PP
	CERT NO.:	250217 - 0810

Table A1: GMW16443 Type I Applications Test Data Form

Section	Test	Requirements	Sample	Visual Edge Adhesion
	3.5.3 Initial, As Received - 24 hrs @ RT		1	Stable, No Lifting or Removal
3.5.3			2	Stable, No Lifting or Removal
			3	Stable, No Lifting or Removal
	3.5.4 Heat Aged 168 hrs @ 80°C per ISO 188, Per Section 3.3	1	Stable, No Lifting or Removal	
3.5.4 Heat Aged 168 hrs @ 80ºC per ISO 18		2	Stable, No Lifting or Removal	
		umidity 168 hrs @ 38ºC / 100% RH per GMW 14729 Option B	3	Stable, No Lifting or Removal
3 5 5			1	Stable, No Lifting or Removal
	5.5 Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option B		2	Stable, No Lifting or Removal
			3	Stable, No Lifting or Removal

Section	Test	Standard	Requirements	Sample	Result
			85% Tape Wet Out	1	
	Tape Wet Out, GMW15851			2	
			3		
	Release Liner Contact	To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
				2	TBD
				3	TBD
	Liner Removal ISO 8510-2		1		
		ISO 8510-2	Less Than or Equal To 65 N/m	2	
				3	

Aug 18

 $\ensuremath{\mathbb{C}}$ Copyright 2017 General Motors Company All Rights Reserved