

250 Chester Street Painesville, Ohio 44077 866-GO-AVERY (866-462-8379) Phone: Fax: 888-358-4469 email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST R	EP	ORT
--------	----	-----

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

FT 1903 PET FOAM PAINTED METAL 250217 - 0910



GMW 16443-TYPE-I

OEM Rev Date: Aug 18 Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

TAPE REQUIREMENTS: 3.5.1 Type I Exposure SECTION 3.3.3 Edge Adhesion 3.5.3, Initial, As Received - 24 hrs @ RT

Specification Securely Bonded

Results Stable, No Lifting or Removal

Stable, No Lifting or Removal

Status Pass

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188,

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option

Securely Bonded

Securely Bonded

Stable, No Lifting or Removal

Pass

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 2-17-2025

Page 1 of 1

1-1-24

Pass

GMW	16443
-----	-------

	PRODUCT:	FT 1903
Appendix A Table A1	SUPPORT:	PET FOAM
	SUBSTRATE:	PAINTED METAL
	CERT NO .:	250217 - 0910

Table A1: GMW16443 Type I Applications Test Data Form

Section	Test	Requirements	Sample	Visual Edge Adhesion
3.5.3 Initial, As Received - 24 hrs @ RT		s @ RT	1	Stable, No Lifting or Removal
	Initial, As Received - 24 hrs @ RT		2	Stable, No Lifting or Removal
		3	Stable, No Lifting or Removal	
3.5.4 Heat Aged 168 hrs @		@ 80ºC per ISO 188, Per Section 3.3	1	Stable, No Lifting or Removal
	Heat Aged 168 hrs @ 80ºC per ISO 188,		2	Stable, No Lifting or Removal
			3	Stable, No Lifting or Removal
3.5.5			1	Stable, No Lifting or Removal
	Humidity 168 hrs @ 38ºC / 100% RH per GMW 14729 Option B		2	Stable, No Lifting or Removal
			3 Stable, No Lifting or Removal	Stable, No Lifting or Removal

Section	Test	Standard	Requirements	Sample	Result
3.6 Tape Wet Out, GMW15851				1	
	Tape Wet Out, GMW15851	- 85% Tape Wet Out	85% Tape Wet Out	2	
				3	
Release Liner Contact				1	TBD
	To Be Determined @ Tier	No Lift Prior To Vehicle Install	2	TBD	
				3	TBD
	Liner Removal ISO 8510-2		Less Than or Equal To 65 N/m	1	
		ISO 8510-2		2	
				3	

Aug 18

 $\ensuremath{\mathbb{C}}$ Copyright 2017 General Motors Company All Rights Reserved