



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 2018X
SUPPORT: PEU FOAM
SUBSTRATE: 20% TALC PP
CERT NO.: 221215 - 1306

GMW 16443 TYPE-I
OEM Rev Date: Oct 16
Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam
Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION 3.3 Edge Adhesion

3.5.3, Initial, As Received

Specification Results Status
Securely Bonded Stable, No Lifting or Removal Pass

3.5.4, Heat Aged, ISO 188 07, 168 hrs @ 80°C

Securely Bonded Stable, No Lifting or Removal Pass

3.5.5, Humidity, GMW 14729 10 Option B, 168 hrs @ 40°C / 100% RH

Securely Bonded Stable, No Lifting or Removal Pass

CERTIFIED BY:

[Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.