

250 Chester StreetPainesville, Ohio 44077Phone:866-GO-AVERY (866-462-8379)Fax:888-358-4469email:psa.tape@averydennison.comURL:tapes.averydennison.com

TEST REPORT

 PRODUCT:
 FT 7951X

 SUPPORT:
 2 MIL PET

 SUBSTRATE:
 PP

 CERT NO.:
 230109 - 1103

ANSI National Accreditation Board

GMW 16443-TYPE-I

OEM Rev Date: Aug 18 Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

TAPE REQUIREMENTS:3.5.1 Type I ExposureSECTION3.3.3 Edge Adhesion3.5.3, Initial, As Received - 24 hrs @ RT

Specification Securely Bonded

Stable, No

<u>Results</u> Stable, No Lifting or Removal

Stable, No Lifting or Removal

Status Pass

Pass

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option

Securely Bonded

Securely Bonded

Stable, No Lifting or Removal

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Techniclan

ISSUE DATE:



Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 6-25-2021

-2021 Page 1 of 1

	PRODUCT:	FT 7951X
Appendix A Table A1	SUPPORT:	2 MIL PET
	SUBSTRATE:	PP
	CERT NO.:	230109 - 1103

Table A1: GMW16443 Type I Applications Test Data Form

Section	Test	Requirements	Sample	Visual Edge Adhesion
3.5.3 Initial, As Receiv			1	Stable, No Lifting or Removal
	Initial, As Received - 24 hrs @ RT		2	Stable, No Lifting or Removal
		Per Section 3.3	3	Stable, No Lifting or Removal
3.5.4 Heat A	Heat Aged 168 hrs @ 80⁰C per ISO 188		1	Stable, No Lifting or Removal
			2	Stable, No Lifting or Removal
			3	Stable, No Lifting or Removal
3.5.5	Humidity 168 hrs @ 38ºC / 100% RH per GMW 14729 Option A		1	Stable, No Lifting or Removal
			2	Stable, No Lifting or Removal
			3	Stable, No Lifting or Removal

Section	Test	Standard	Requirements	Sample	Result
3.6 Tape Wet Out GMW15851			- 85% Tape Wet Out	1	Not Tested
	Tape Wet Out, GMW15851	- 85% Tape Wet Out		2	Not Tested
			3	Not Tested	
371		Release Liner Contact To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
	Release Liner Contact			2	твр
				3	твр
3.7.2	Liner Removal ISO 8510-2		Less Than or Equal To 65 N/m	1	Not Tested
		ISO 8510-2		2	Not Tested
				3	Not Tested

Aug 18

© Copyright 2017 General Motors Company All Rights Reserved