

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone: Fax:


email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO.: **FT 8327** EPDM FOAM PAINTED METAL 221215 - 1135



OEM Rev Date: Dec 10 Adhesion Performance Requirements For Adhesive Backed Foam Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle



## TAPE REQUIREMENTS:

3.5.1 Type I Exposure SECTION 3.3 Edge Adhesion	Specification	Results	<u>Status</u>
3.3, Initial, As Received	Securely Bonded	Stable, No Lifting or Removal	Pass
3.5.4, Heat Aged, ISO 188, 168 hrs @ 80C	Securely Bonded	Stable, No Lifting or Removal	Pass
3.5.5, GMW 14729 Humidity, Option B - 168 hrs @ 40C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: