



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBR 8950
 SUPPORT: EPDM FOAM
 SUBSTRATE: PC ABS
 CERT NO.: 221215 - 1157



GMW 16443 TYPE-I
 OEM Rev Date: May 15
 Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam

TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION 3.3 Edge Adhesion

3.5.3, Initial, As Received

| <u>Specification</u> | <u>Results</u> | <u>Status</u> |
|------------------------|-------------------------------|---------------|
| Securely Bonded | Stable, No Lifting or Removal | Pass |

3.5.4, Heat Aged, ISO 188 07, 168 hrs @ 80°C

| | | |
|------------------------|-------------------------------|-------------|
| Securely Bonded | Stable, No Lifting or Removal | Pass |
|------------------------|-------------------------------|-------------|

3.5.5, Humidity, GMW 14729 10 Option B, 168 hrs @ 40°C / 100% F

| | | |
|------------------------|-------------------------------|-------------|
| Securely Bonded | Stable, No Lifting or Removal | Pass |
|------------------------|-------------------------------|-------------|

CERTIFIED BY:



Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.