



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: **FBA 8960**  
 SUPPORT: **0.5 MM FELT**  
 SUBSTRATE: **PC ABS**  
 CERT NO.: **221215 - 1157**



**GMW 16443 TYPE-I**

OEM Rev Date: Sep 17

Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam

Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

**TAPE REQUIREMENTS:**

**3.5.1 Type I Exposure**

SECTION **3.3.3 Edge Adhesion**

3.5.3, Initial, As Received - 24 hrs @ RT

Specification  
**Securely Bonded**

Results  
 Stable, No Lifting or Removal

Status  
**Pass**

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188,

**Securely Bonded**

Stable, No Lifting or Removal

**Pass**

3.5.5, After Humidity 168 hrs @ 38°C / 100% RH per GMW 1472

**Securely Bonded**

Stable, No Lifting or Removal

**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

## Appendix A Table A1

PRODUCT: **FBA 8960**  
 SUPPORT: **0.5 MM FELT**  
 SUBSTRATE **PC ABS**  
 CERT NO.: 221215 - 1157

Table A1: GMW16443 Type I Applications Test Data Form

| Section | Test   | Requirements    | Sample | Visual Edge Adhesion          |
|---------|--|-----------------|--------|-------------------------------|
| 3.5.3   | Initial, As Received - 24 hrs @ RT                             | Per Section 3.3 | 1      | Stable, No Lifting or Removal |
|         |  |                 | 2      | Stable, No Lifting or Removal |
|         |  |                 | 3      | Stable, No Lifting or Removal |
| 3.5.4   | Heat Aged 168 hrs @ 80°C per ISO 188,                          |                 | 1      | Stable, No Lifting or Removal |
|         |  |                 | 2      | Stable, No Lifting or Removal |
|         |  |                 | 3      | Stable, No Lifting or Removal |
| 3.5.5   | After Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option B |                 | 1      | Stable, No Lifting or Removal |
|         |  |                 | 2      | Stable, No Lifting or Removal |
|         |  |                 | 3      | Stable, No Lifting or Removal |

| Section | Test                   | Standard                | Requirements                     | Sample | Result     |
|---------|------------------------|-------------------------|----------------------------------|--------|------------|
| 3.6     | Tape Wet Out, GMW15851 | #REF!                   | 85% Tape Wet Out                 | 1      |            |
|         |                        |                         |                                  | 2      | #REF!      |
|         |                        |                         |                                  | 3      | #REF!      |
|         | Release Liner Contact  | To Be Determined @ Tier | No Lift Prior To Vehicle Install | 1      | Not Tested |
|         |                        |                         |                                  | 2      | Not Tested |
|         |                        |                         |                                  | 3      | Not Tested |
|         | Liner Removal          | ISO 8510-2              | Less Than Or Equal To 65 N/m     | 1      |            |
|         |                        |                         |                                  | 2      |            |
|         |                        |                         |                                  | 3      |            |