



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FBA 8960**  
SUPPORT: **EPDM FOAM**  
SUBSTRATE: **PAINTED METAL**  
STD CERT NO.: **221215 - 1158**



**GMW 16443 TYPE-I**  
OEM Rev Date: Dec 10  
Adhesion Performance Requirements For Adhesive Backed Foam  
TYPE I - An adhesive backed foam composite that is entrapped and/or  
mechanically retained for the life of the vehicle

**TAPE REQUIREMENTS:**

**3.5.1 Type I Exposure**

**SECTION 3.3 Edge Adhesion**

3.53, Initial, As Received

| <u>Specification</u>   | <u>Results</u>                | <u>Status</u> |
|------------------------|-------------------------------|---------------|
| <b>Securely Bonded</b> | Stable, No Lifting or Removal | <b>Pass</b>   |

3.54, Heat Aged, ISO 188 07, 168 hrs @ 80C

|                        |                               |             |
|------------------------|-------------------------------|-------------|
| <b>Securely Bonded</b> | Stable, No Lifting or Removal | <b>Pass</b> |
|------------------------|-------------------------------|-------------|

3.55, GMW 14729 Humidity, Option B - 168 hrs @ 40C / 100% RH

|                        |                               |             |
|------------------------|-------------------------------|-------------|
| <b>Securely Bonded</b> | Stable, No Lifting or Removal | <b>Pass</b> |
|------------------------|-------------------------------|-------------|

CERTIFIED BY:

**Dave Nichols Jr, Automotive Lab Technician**

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.