



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: stus.averydennison.com

TEST REPORT

PRODUCT: FT 0900X
SUPPORT: FLOCK
SUBSTRATE: PP
STD CERT NO.: 221215 - 1457



GMW 16875 TYPE IA-CYCLE-D
OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape
Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV Initial

TAPE REQUIREMENTS:

| SECTION: | Standard | Specification | Results | Status |
|--|--------------------------|--|---|----------------------|
| Initial RT | ISO 8510-2 | 900 N / m | 41.4 | Pass |
| SECTION: Peel Adhesion Aged, 72 hrs @ RT | ISO 8510-2 | 350 N / m | 1268.9 | Pass |
| Humidity, 24 hrs @ 38°C / 95% RH | | 350 N / m | 1543.8 | Pass |
| Aged, 168 hrs @ 70°C | | 350 N / m | 403.9 | Pass |
| GMW 14124 CYCLE D | | 350 N / m | 567.9 | Pass |
| 24 hrs @ 38°C / 100% RH 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C | | | | |
| SECTION: Shear Strength, MD 4 hrs @ -18°C | ASTM D1000 | 7500 N / m | 14563.1 | Pass |
| 24 hrs @ 60°C | | 3500 N / m | 6271.5 | Pass |
| SECTION: Taber Abrasion* 500 Cycles CS-10,1 kg Load | GMW3208 | No Wear Thru to Fabric Backing | Worn But Not Thru | Pass |
| SECTION: Flammability Initial, Component | GMW3232 | 100 mm / min | < B 25 | Pass |
| SECTION: Xenon Weatherometer* Not Applicable | GMW14162 | No Degradation, Stiffening, Bleaching or Objectionable Color | Not Applicable | NA |
| SECTION: Odor* Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C | GMW3205 | 6 Min Rating | 9 Just Noticeable 9 Just Noticeable 9 Just Noticeable | Pass Pass Pass |
| SECTION: VOC* Per GMW 16853 | GMW15634 | 6 mg | Not Tested | NA |
| SECTION: Gravimetric Fogging Initial, Component | GMW3235 Method B - HAAKE | 2 mg | 0.958 | Pass |

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.