

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL:

stus.averydennison.com

TEST REPORT

FT 0900X PET PRODUCT: **FLOCK**

SUPPORT: SUBSTRATE: PP

STD CERT NO.: 221215 - 1457

GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

TESTING LABORATORY



SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 29.2	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	<u>Results</u> 960.7	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	1162.1	Pass
Aged, 168 hrs @ 70°C		350 N/m	362.5	Pass
GMW 14124 CYCLE D 24 hrs @	38°C / 100% RH	350 N/m	486.8	Pass

4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C

100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	<u>Specification</u>	Results	<u>Status</u>
4 hrs @ -18°C		7500 N/m	14211.7	т Pass
24 hrs @ 60°C		3500 N/m	4868.4	Pass

SECTION: Taber Abrasion*	GMW3208	Specification	Results	Status
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass

SECTION: Flammability	GMW3232	Specification	Results	<u>Status</u>
Initial, Component		100 mm / min	< B 25	Pass

SECTION: Xenon Weatherometer*	GMW14162	Specification	Results	Status
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor*	GMW3205	Specification	Results	<u>Status</u>
Wet Condition, Coding A - 24 hrs @	70°C, Deionized Water	6 Min Rating	9 Just Noticeable	Pass
Dry Condition, Coding B - 24 hrs @	70°C		9 Just Noticeable	Pass
High Temp Condition - 24 hrs @ 10	5°C		9 Just Noticeable	Pass

SECTION: VOC*	GMW15634	Specification	Results	<u>Status</u>
Per GMW 16853		6 mg	Not Tested	NA

SECTION: Gravimetric Fogging	GMW3235 Method B - HAAKE	Specification	Results	<u>Status</u>
Initial, Component		2 mg	0.958	Pass

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.