



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT A902
SUPPORT: FLOCK
SUBSTRATE: PP
STD CERT NO.: 240109 - 1434



GMW 16875 TYPE IA-CYCLE-D
OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape
Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV Initial

TAPE REQUIREMENTS:

SECTION:	ISO	Specification	Results	Status
Liner Removal Initial RT	ISO 8510-2	900 N / m	39.3	Pass
Peel Adhesion Aged, 72 hrs @ RT Humidity, 24 hrs @ 38°C / 95% RH Aged, 168 hrs @ 70°C GMW 14124 CYCLE D 24 hrs @ 38°C / 100% RH 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C	ISO 8510-2	350 N / m	682.6 959.1 898.5 879.7	Pass Pass Pass Pass
Shear Strength, MD 4 hrs @ -18°C 24 hrs @ 60°C	ASTM D1000	7500 N / m 3500 N / m	8994.6 6228.2	Pass Pass
Taber Abrasion* 500 Cycles CS-10,1 kg Load	GMW3208	No Wear Thru to Fabric Backing	Worn But Not Thru	Pass
Flammability Initial, Component	GMW3232	100 mm / min	< B 25	Pass
Xenon Weatherometer* Not Applicable	GMW14162	No Degradation, Stiffening, Bleaching or Objectionable Color	Not Applicable	NA
Odor* Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C	GMW3205	6 Min Rating	Not Tested Not Tested Not Tested	Not Tested Not Tested Not Tested
VOC* Per GMW 16853	GMW15634	6 mg	Not Tested	NA
Gravimetric Fogging 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant	GMW3235 Method B	2 mg	1.2	Pass

CERTIFIED BY:
David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.