250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

 PRODUCT:
 FT A912

 SUPPORT:
 FLOCK

 SUBSTRATE:
 ABS

 STD CERT NO.:
 230913 - 0849



GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV Initial

TAPE REQUIREMENTS: SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N / m	Results 18.7	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N / m	<u>Results</u> 1194.8	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	1240.1	Pass
Aged, 168 hrs @ 70°C		350 N/m	1247.2	Pass
GMW 14124 CYCLE D 24 hrs @ 3	38°C / 100% RH	350 N/m	1230.3	Pass

24 hrs @ 38°C / 100' 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C

SECTION: Shear Strength, MD 4 hrs @ -18°C	ASTM D1000	Specification 7500 N / m	<u>Results</u> 10850.4	Status T Pass
24 hrs @ 60°C		3500 N/m	9628.7	т Pass
SECTION: Taber Abrasion* 500 Cycles CS-10,1 kg Load	GMW3208	Specification No Wear Thru to Fabric Backing	<u>Results</u> Worn But Not Thru	Status Pass
SECTION: Flammability Initial, Component	GMW3232	Specification 100 mm / min	Results < B 25	Status Pass
SECTION: Xenon Weatherometer* Not Applicable	GMW14162	Specification No Degradation, Stiffening, Bleaching or Objectionable Color	Results Not Applicable	Status NA
SECTION: Odor* Wet Condition, Coding A - 24 hrs @ 70°C, Do Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C	GMW3205 eionized Water	Specification 6 Min Rating	Results Not Tested Not Tested Not Tested	Status NT NT NT
SECTION: VOC*	GMW15634	Specification	Results	Status

6 mg

Specification

< 2 mg

Per GMW 16853

CERTIFIED BY:

SECTION: Gravimetric Fogging GMW3235 Method B 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant

D/1/4

ISSUE DATE:

1-1-25

Not Tested

Results

1.8

NA

Status

Pass

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: