

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT A912 SUPPORT: **FLOCK** PP SUBSTRATE:

230913 - 0849 STD CERT NO.:

## **GMW 16875 TYPE IA-CYCLE-D**

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

ACCREDITED

TESTING LABORATORY

**Pass** 

**Status** 

Initial



SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 18.2	Status Pass
SECTION: <b>Peel Adhesion</b> Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	Results 515.8	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	553.7	Pass
Aged, 168 hrs @ 70°C		350 N/m	530.6	Pass
GMW 14124 CYCLE D 24 hrs @ 4 hrs @	38°C / 100% RH 85°C	350 N/m	524.4	Pass

3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C

100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	Specification	Results	Status
4 hrs @ -18°C		7500 N/m	10824.1	т Pass

3500 N/m 6487.5 24 hrs @ 60°C

SECTION: Taber Abrasion*	GMW3208	Specification	Results	Status
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass

**SECTION: Flammability** Specification Results GMW3232 Status 100 mm / min SE/NBR Initial, Component **Pass** 

**SECTION: Xenon Weatherometer\*** GMW14162 Specification Results **Status** Not Applicable No Degradation, Stiffening, Not Applicable NA **Bleaching or Objectionable Color** 

SECTION: Odor\* Specification Results GMW3205 **Status** Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water 6 Min Rating Not Tested NT Dry Condition, Coding B - 24 hrs @ 70°C Not Tested NT

High Temp Condition - 24 hrs @ 105°C Not Tested NT SECTION: VOC\* GMW15634 Specification Results

Per GMW 16853 6 mg Not Tested NA **SECTION: Gravimetric Fogging** GMW3235 Method B Specification Results **Status** 

18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 2 ma 1.8 **Pass** 

**CERTIFIED BY:** 



1-1-25 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

1-1-1904