

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com

URL: stus.averydennison.com

TEST REPORT

PRODUCT: FT 1149X 2 MM FELT SUPPORT: PP

SUBSTRATE:

221216 - 0933 STD CERT NO.:

GMW 16875 TYPE IA-CYCLE-E


OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

TESTING LABORATORY

Initial



SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	<u>Results</u> 30.9	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 350 N/m	<u>Results</u> 1456.2	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N/m	1704.9	Pass
Aged, 168 hrs @ 70°C		350 N/m	2199.8	Pass
GMW 14124 CYCLE E		350 N/m	2116.4	Pass

72 hrs @ 70°C

24 hrs @ 38°C / 100% RH

8 hrs @ -30°C

40 hrs @ 70°C

24 hrs @ 38°C / 100% RH

8 hrs @ -30°C

SECTION: Shear Strength, MD 4 hrs @ -18°C	ASTM D1000	Specification 7500 N/m	Results 10996.3	Status Pass
24 hrs @ 60°C		3500 N/m	4371.7	Pass
SECTION: Taber Abrasion* 500 Cycles CS-10,1 kg Load	GMW3208	Specification No Wear Thru to Fabric Backing	Results Worn But Not Thru	Status Pass
SECTION: Flammability Initial, Component	GMW3232	Specification 100 mm/min	Results	Status Pass

Initial, Component		100 mm / min		Pass
SECTION: Xenon Weatherometer* Not Applicable	GMW14162	Specification No Degradation, Stiffening, Bleaching or Objectionable Color	Results Not Applicable	Status NA

SECTION: Odor* Specification Results GMW3205 Status Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water 6 Min Rating 8 Noticeable, Trace Pass Dry Condition, Coding B - 24 hrs @ 70°C 8 Noticeable, Trace **Pass** High Temp Condition - 24 hrs @ 105°C 7 Clearly Noticeable, But Not Objectionable **Pass**

Specification SECTION: VOC* GMW15634 Results Status Per GMW 16853 6 mg Not Tested **Not Tested**

Specification **SECTION: Gravimetric Fogging** GMW3235 Method B Results **Status** 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 2 mg 1.8 **Pass**

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.