	AVERY DENNISON
--	-------------------

250 Chester Street				
Painesville, Ohio 44077				
Phone:	866-GO-AVERY (866-462-8379)			
Fax:	888-358-4469			
email:	psa.tape@averydennison.com			
URL:	stus.averydennison.com			

TEST REPORT

 PRODUCT:
 FT 8392

 SUPPORT:
 0.5 MM FELT

 SUBSTRATE:
 PC ABS

 STD CERT NO.:
 221216 - 0931



GMW 16875 TYPE IA-CYCLE-E

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV Initial

ISO 8510-2	Specification 900 N / m	Results 11.1	<u>Status</u> Pass
ISO 8510-2	Specification 350 N / m	<u>Results</u> 969.5	<u>Status</u> Pass
	350 N / m	798.5	Pass
	350 N / m	637.4	Pass
70°C 38°C / 100% RH	350 N / m	631.5	Pass
	ISO 8510-2 70°C 38°C / 100% RH	900 N / m ISO 8510-2 350 N / m 350 N / m 350 N / m 350 N / m 350 N / m	900 N/m 11.1 ISO 8510-2 Specification 350 N/m Results 969.5 350 N/m 798.5 350 N/m 637.4 350 N/m 631.5

8 hrs @ -30°C 40 hrs @ 70°C 24 hrs @ 38°C / 100% RH

8 hrs @ -30°C

SECTION: Shear Strength, MD	ASTM D1000	Specification	<u>Results</u>	<u>Status</u>
4 hrs @ -18°C		7500 N / m	7759.3	т Pass
24 hrs @ 60°C		3500 N / m	7161.0	т Pass
SECTION: Taber Abrasion*	GMW3208	Specification	Results	<u>Status</u>
500 Cycles CS-10,1 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass
SECTION: Flammability	GMW3232	Specification	Results	<u>Status</u>
Initial, Component		100 mm / min	DNI	Pass
SECTION: Xenon Weatherometer* Not Applicable	GMW14162	<u>Specification</u> No Degradation, Stiffening, Bleaching or Objectionable Color	Results_ Not Applicable	Status NA
SECTION: Odor* Wet Condition, Coding A - 24 hrs @ 70°C, Dei Dry Condition, Coding B - 24 hrs @ 70°C	GMW3205 onized Water	Specification 6 Min Rating	Results 8 Noticeable, Trace 8 Noticeable, Trace	<u>Status</u> Pass Pass

High Temp Condition - 24 hrs @ 105°C 7 Clearly Noticeable, But Not Objectionable Pass GMW15634 Specification Results SECTION: VOC* Status Per GMW 16853 6 mg Not Tested NA Specification SECTION: Gravimetric Fogging GMW3235 Method B Results Status 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 2 mg 1.9 Pass

ISSUE DATE:

1-1-25

Dave Nichols Jr, Automotive Lab Technician

CERTIFIED BY:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date:

9-9-2020 Page 1 of 1