

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL: tapes.averydennison.com

## **TEST REPORT**

FT A902 PRODUCT: SUPPORT: **FLOCK** PP SUBSTRATE:

230926 - 0714 STD CERT NO.:

ACCREDITED TESTING LABORATORY

**Status** 

**Pass** 

**Pass** 

## **GMW 16875 TYPE II-CYCLE-D**

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV

TAPE RE	QUIRE	MENTS:
---------	-------	--------

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 39.3	Status Pass
SECTION: <b>Peel Adhesion</b> Aged, 72 hrs @ RT	ISO 8510-2	Specification 280 N/m	Results 682.6	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		280 N/m	959.1	Pass
Aged, 168 hrs @ 70°C		280 N/m	898.5	Pass
GMW 14124 CYCLE D 24 hrs @	38°C / 100% RH	280 N/m	879.7	Pass

4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C

SECTION: Shear Strength, MD	ASTM D1000	Specification	Results
4 hrs @ -18°C		2500 N/m	8994.6

24 hrs @ 60°C	2500 N/m	6228.2	F

SECTION: Taber Abrasion*	GMW3208	Specification	Results	Status
500 Cycles CS-10,0.5 kg Load		No Wear Thru to Fabric Backing	Worn But Not Thru	Pass

SECTION: Flammability	GMW3232	<u>Specification</u>	Results	<u>Status</u>
Initial, Component		100 mm / min	< B 25	Pass

SECTION: Xenon Weatherometer*	GMW14162	Specification	Results	Status
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor*	GMW3205	Specification	Results	<u>Status</u>
Wet Condition, Coding A - 24 hrs @	70°C, Deionized Water	6 Min Rating	Not Tested	NT
Dry Condition, Coding B - 24 hrs @	70°C		Not Tested	NT
High Temp Condition - 24 hrs @ 10	5°C		Not Tested	NT

SECTION: VOC*	GMW15634	Specification_	Results	Status
Per GMW 16853		6 ma	Not Tested	NΔ

1 01 011111 10000				
OF OTION Considerately Foundation	01111000511111	Charification	Desults	<b>0.</b> .
SECTION: Gravimetric Fogging	GMW3235 Method B	Specification	Results	Status

18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant Pass 2 mg 1.2

CERTIFIED BY:



ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.