	AVERY DENNISON
--	-------------------

 250 Chester Street

 Painesville, Ohio 44077

 Phone:
 866-GO-AVERY (866-462-8379)

 Fax:
 888-358-4469

 email:
 psa.tape@averydennison.com

 URL:
 tapes.averydennison.com

TEST REPORT

 PRODUCT:
 UHMW 327

 SUPPORT:
 POLYETHYLENE

 SUBSTRATE:
 PP

 STD CERT NO.:
 240717 - 0747



GMW 16875 TYPE II-CYCLE-D OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type II material is a nonwoven tape coated with a permanent acrylic PSA Initial

TAPE REQUIREMENTS: SECTION: Liner Removal Initial RT	2 Specification 900 N / m	Results 5.8	<u>Status</u> Pass
SECTION: Peel Adhesion ISO 8510-2 Aged, 72 hrs @ RT	2 Specification 280 N / m	<u>Results</u> 303.0	<u>Status</u> Pass
Humidity, 24 hrs @ 38°C / 95% RH	280 N / m	623.0	Pass
Aged, 168 hrs @ 70°C	280 N/m	866.2	Pass
GMW 14124 CYCLE D 24 hrs @ 38°C / 100% Rł 4 hrs @ 85°C 3 hrs @ RT	280 N / m H	701.5	Pass

SECTION: Shear Strength, MD	ASTM D1000	Specification	<u>Results</u>	<u>Status</u>
4 hrs @ -18°C		2500 N / m	2706.6	Pass
24 hrs @ 60°C		2500 N / m	3409.4	Pass
SECTION: Taber Abrasion*	GMW3208	Specification	<u>Results</u>	<u>Status</u>
500 Cycles CS-10,0.5 kg Load		No Wear Thru to Fabric Backing	Not Tested	Not Tested

Specification

100 mm / min

Specification

No Degradation, Stiffening,

Bleaching or Objectionable Color

Specification

6 Min Rating

Specification

6 mg

Specification

< 2 mg

SECTION: Flammability Initial, Component

SECTION: Xenon Weatherometer* Not Applicable

SECTION: **Odor*** GMW3205 Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C

SECTION: VOC* Per GMW 16853

SECTION: Gravimetric Fogging GMW3235 Method B 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant

CERTIFIED BY:

17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C

GMW3232

GMW14162

GMW15634

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-25

1-1-20

Results

< B 25

Results

Not Applicable

Results

Not Tested

Not Tested

Not Tested

Results

Not Tested

Results

0.6

Status

Pass

Status

NA

Status

Not Tested

Not Tested

Not Tested

Status

NA

Status

Pass

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: