

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **UHMW 527UV PET** SUPPORT: **POLYETHYLENE**

SUBSTRATE:

STD CERT NO.: 240717 - 0816

GMW 16875 TYPE II-CYCLE-D

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type II material is a nonwoven tape coated with a permanent acrylic PSA

Initial

TAPE	REQUIREMENTS:
IAFE	REQUIRENIEN 13.

SECTION: Liner Removal Initial RT	ISO 8510-2	Specification 900 N/m	Results 5.4	Status Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	Specification 280 N/m	<u>Results</u> 315.8	Status Pass
Humidity, 24 hrs @ 38°C / 95% RH		280 N/m	416.9	Pass
Aged, 168 hrs @ 70°C		280 N/m	333.4	Fail
4 hrs @ 3 hrs @	RT	280 N/m	439.2	Pass
17 hrs @ 168 hrs @				

SECTION: Shear Strength, MD 4 hrs @ -18°C	ASTM D1000	Specification 2500 N/m	Results 3878.7	Status Pass
24 hrs @ 60°C		2500 N/m	3600.7	Pass
SECTION: Taber Abrasion* 500 Cycles CS-10,0.5 kg Load	GMW3208	Specification No Wear Thru to Fabric Backing	Results Not Tested	Status Not Tested
SECTION: Flammability Initial, Component	GMW3232	Specification 100 mm/min	Results < B 25	Status Pass

SECTION: Xenon Weatherometer*	GMW14162	Specification	Results	<u>Status</u>
Not Applicable		No Degradation, Stiffening,	Not Applicable	NA
		Bleaching or Objectionable Color		

SECTION: Odor*	GMW3205	Specification	Results	<u>Status</u>
Wet Condition, Coding A - 24 hrs @ 70°C	, Deionized Water	6 Min Rating	Not Tested	Not Tested
Dry Condition, Coding B - 24 hrs @ 70°C			Not Tested	Not Tested
High Temp Condition - 24 hrs @ 105°C			Not Tested	Not Tested

SECTION: VOC*	GMW15634	Specification	Results	<u>Status</u>
Per GMW 16853		6 mg	Not Tested	NA

SECTION: Gravimetric Fogging GMW3235 Method B **Specification** Results **Status** 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant 0.7 < 2 mg **Pass**

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

4 hrs @ -30C 100 hrs @ 70°C

> ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

ACCREDITED

TESTING LABORATORY