



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

email: psa.tape@averydennison.com URL:

stus.averydennison.com

PRODUCT: FT 8217 SUPPORT: 3 MM FELT SUBSTRATE: ABS

STD CERT NO.: 221216 - 0938

GMW 16875 TYPE II-CYCLE-E

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape Type II material is a nonwoven tape coated with a permanent acrylic PSA ACCREDITED

TESTING LABORATORY

Page 1 of 1

Initial

TAPE	REQU	IREME	NTS:
------	------	-------	------

Specification SECTION: Liner Removal ISO 8510-2 Results **Status** Initial RT 900 N/m 18.7 **Pass** SECTION: Peel Adhesion **Specification** ISO 8510-2 Results **Status** Aged, 72 hrs @ RT 280 N/m 1497.1 **Pass** 280 N/m Humidity, 24 hrs @ 38°C / 95% RH 1775.5 **Pass** Aged, 168 hrs @ 70°C 280 N/m 1650.0 **Pass** GMW 14124 CYCLE E 280 N/m 1493.6 **Pass**

72 hrs @ 70°C

24 hrs @ 38°C / 100% RH

8 hrs @ -30°C 40 hrs @ 70°C

24 hrs @ 38°C / 100% RH

8 hrs @ -30°C

SECTION: Shear Strength, MD	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
4 hrs @ -18°C		2500 N/m	9471.2	т Pass

24 hrs @ 60°C 2500 N/m 2697.7 **Pass**

SECTION: Taber Abrasion* GMW3208 **Specification Results Status** No Wear Thru to Fabric Backing Severly Worn But Not Thru 500 Cycles CS-10,0.5 kg Load **Pass**

Specification SECTION: Flammability Results **Status** 100 mm / min 25.0 Initial, Component GMW3232 **Pass**

SECTION: Xenon Weatherometer* Specification GMW14162 Results Status 5 4 1 Not Applicable No Degradation, Stiffening, Not Applicable NA

Bleaching or Objectionable Color

Specification SECTION: Odor* Results **Status**

Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water 6 Min Rating 9 Just Noticeable **Pass** Dry Condition, Coding B - 24 hrs @ 70°C 8 Noticeable, Trace **Pass Pass**

High Temp Condition - 24 hrs @ 105°C ' Clearly Noticeable, But Not Objectionable

SECTION: VOC* Specification Status GMW15634 Results Per GMW 16853 6 mg Not Tested **Not Tested**

SECTION: Gravimetric Fogging GMW3235 Method B - HAAKE **Specification** Results **Status** Initial, Component < 2 mg 0.28 **Pass**

CERTIFIED BY:

1-1-25 ISSUE DATE: Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.