



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **stus.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 0900X**  
 SUPPORT: **FLOCK**  
 SUBSTRATE: **FOIL**  
 STD CERT NO.: **221216 - 0957**



**GMW 3235 Method B**  
 Test Method Rev Date: Aug 16  
 Fogging Characteristics of Trim Materials  
 Y1 Materials with low water absorption (e.g. upholstery, fabrics, foam, artificial leather)  
 T2 100°C  
 Reference Spec : GMW 16875

**TAPE REQUIREMENTS:**

SECTION: <b>Fogging</b>	GMW 3235 Method B	<b>Specification</b>	<b>Results</b>	<b>Status</b>
Product, 18 hrs @ 100°C, 21°C Cooling, 24 hr Desiccator @ RT		<b>≤ 2 mg max</b>	0.125	<b>Pass</b>

Product, 18 hrs @ 100°C, 21°C Cooling, 24 hr Desiccator @ RT	<b>≤ 2 mg max</b>	0.000	<b>Pass</b>
--	-------------------	-------	-------------

Product, 18 hrs @ 100°C, 21°C Cooling, 24 hr Desiccator @ RT	<b>≤ 2 mg max</b>	0.200	<b>Pass</b>
--	-------------------	-------	-------------

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.