



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392
 SUPPORT: PVC FOAM
 SUBSTRATE: LEXAN
 CERT NO.: 221221 - 1310



INTEVA MX650011 Type III

OEM Rev Date: Mar 08
 Adhesion Performance Requirements of Pressure Sensitive Adhesive Coated Parts (Minimal Stress) Type III
 5.3 For a part bonded at a Tier 1 supplier and mechanically fastened on line adhesion:

Passing Type III Meets and Exceeds Type I and II Requirements

TAPE REQUIREMENTS:

4. REQUIREMENTS

SECTION 4.3.1 Creep Resistance

4.3.1, A Initial, Bonded @ 25°C, 50% RH - 7 Days @ 40°C

Specification
No Lifting or Shifting

Results
 Stable, No Lifting or Removal

Status
Pass

SECTION 4.3.2 Peel Adhesion

4.3.2, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification
350 N / m

Results
 1558.0

Status
Pass

SECTION 4.3.3 Impact

4.3.3, A Bonded @ 25°C, 50% RH, - 20 mins @ RT

Specification
No Separation from 2 Impacts

Results
 No Impact Separation

Status
Pass

SECTION 4.3.4 Edge Adhesion

4.3.4, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification
Securely Bonded

Results
 Stable, No Lifting or Removal

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.