



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126
SUPPORT: 2 MIL PET
SUBSTRATE: HDPE
CERT NO.: 230109 - 1110



SUZUKI SES D 2403 CLASS D
OEM Rev Date: Dec 12
Quality Classification of Pressure Sensitive Adhesive Film for Decoration

TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
6.2, 24 hrs @ 80°C	No Edge Peeling or Separation of Paper	No Edge Lifting, Separation or Delamination	Pass
6.3, Initial, 24 hrs @ RT	8 N / 25 mm	21.4	Pass
6.4, Normal, 10 mins @ RT	14 N / 25 mm	21.9	Pass
6.5.1, Accelerated Test, Weatherability, WAN-1, 1000 hrs	No Separation, Edge Ooze, Color or Deformation Change	Not Tested	NT
6.5.2, Outdorr Exposure, Weatherability, WON, 12 months		Not Tested	NT
6.5.1, Accelerated Test, Weatherability, WAN-1, 1000 hrs	14 N / 25 mm	Not Tested	NT
6.5.2, Outdorr Exposure, WON, 12 months, Cross-cut	14 N / 25 mm	Not Tested	NT
6.6.1, Test A, 96 hrs @ 80°C, 1 hr @ RT	No Change in Appearance or Discoloration	No Wrinkling, Cracking Or Color Changes	Pass
6.6.2, Test B, 4 hrs @ 100°C, 1 hr @ RT		No Wrinkling, Cracking Or Color Changes	Pass
6.6.3, Test C, 2 hrs @ 140°C, 1 hr @ RT		HDPE Melted - No Testing	NT
6.6.1, Test A, 96 hrs @ 80°C, "Normal"	14 N / 25 mm	22.1	Pass
6.6.2, Test B, 4 hrs @ 100°C, Normal	14 N / 25 mm	17.2	Pass
6.6.3, Test C, 2 hrs @ 140°C, Cross-cut	14 N / 25 mm	HDPE Melted - No Testing	NT
6.7, Cycles 5X	No Change in Appearance or Discoloration	No Wrinkling, Cracking Or Color Changes	Pass
3 hrs @ -30°C, 1 hr @ RT, 3 hrs @ 80°C, 1 hr @ RT, 15 hrs @ 50°C / 98% RH, 1 hr @ RT			
6.7, Cycles 5X, Normal	14 N / 25 mm	32.4	Pass
6.8, 168 hrs @ 50°C / 95% RH	No Separation, Edge Ooze, Color or	No Ooze, Lifting or Delamination	Pass
6.8, 168 hrs @ 50°C / 95% RH	14 N / 25 mm	29.6	Pass
6.9, Immersed 96 hrs @ 40°C	No Separation, Edge Ooze, Color or	No Ooze, Lifting or Delamination	Pass
6.9, Immersed 96 hrs @ 40°C, Normal	14 N / 25 mm	32.7	Pass
6.10, Immersed 96 hrs @ 40°C	No Separation, Edge Ooze, Color or	No Ooze, Lifting or Delamination	Pass
6.10, Immersed 96 hrs @ 40°C, Normal	14 N / 25 mm	33.9	Pass
6.19, 30 mins @ 23°C	No Cracks or Separation	No Separation	Pass
6.19, 30 mins @ -15°C		No Separation	Pass
6.22, 48 hrs @ 80°C	No Failure or Separation	No Edge Lifting, Separation or Delamination	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.