



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392 12 PT BD
SUPPORT: PVC FOAM
SUBSTRATE: ABS
CERT NO.: 221221 - 1443

TOYOTA TSK 6505G - 2A1
OEM Rev Date: Mar 96
Toyota Engineering Standard - Caulking, Sponge, Sealants
2A1 - Semi-close cell type synthetic rubber (Soft)
Acrylic Based

TAPE REQUIREMENTS:

SECTION: 4.11.1 Peel Adhesion (T-Peel Adhesion *)

4.11.1, Initial, 5 mins As Received

Table with 4 columns: Specification (Cohesive Failure), ASTM D1876, Results (Cohesive Split), Status (Pass)

SECTION: 4.11.2 Peel Adhesion

4.11.2, Peel Adhesion, Initial, 5 mins As Received

Table with 4 columns: Specification (6.9 N / 15 mm), ASTM D3330, Results (7.0), Status (Pass)

4.11.2, Peel Adhesion, 24 hrs @ RT

Table with 4 columns: Specification (6.9 N / 15 mm), Results (7.7), Status (Pass)

4.11.2, Peel Adhesion, High Temp, 24 hrs @ 80°C

Table with 4 columns: Specification (6.9 N / 15 mm), Results (9.0), Status (Pass)

4.11.2, Peel Adhesion, Water Immersed, 10 days @ 40°C, 1 hr @ RT

Table with 4 columns: Specification (6.9 N / 15 mm), Results (12.5), Status (Pass)

CERTIFIED BY:

Signature of Dave Nichols Jr.
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.