



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1126
SUPPORT: EPDM FOAM
SUBSTRATE: HDPE
CERT NO.: 221221 - 1459



TOYOTA TSK 6505G - 2B1
OEM Rev Date: Mar 96
Toyota Engineering Standard - Caulking, Sponge, Sealants
2B1 - Semi-close cell type synthetic rubber (Hard)
Acrylic Based

TAPE REQUIREMENTS:

SECTION: 4.11.1 Peel Adhesion (T-Peel Adhesion)

4.11.1, Initial, 5 mins As Received

Specification ASTM D1876 Results Cohesive Split Status Pass

SECTION: 4.11.2 Peel Adhesion

4.11.2, Peel Adhesion, Initial, 5 mins As Received

Specification ASTM D3330 Results 7.7 Status Pass

4.11.2, Peel Adhesion, 24 hrs @ RT

2.0 N / 15 mm 9.8 Pass

4.11.2, Peel Adhesion, High Temp, 24 hrs @ 80°C

2.0 N / 15 mm 2.6 Pass

4.11.2, Peel Adhesion, Water Immersed, 10 days @ 40°C, 1 hr @ RT

2.0 N / 15 mm 7.1 Pass

CERTIFIED BY:

[Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.