



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FBD 8970**
 SUPPORT: **PEU FOAM**
 SUBSTRATE: **SS**
 CERT NO.: **221222 - 0735**



TOYOTA TSK 6712G -1A- 30-N-LT
 OEM Rev Date: Sep 05
 Toyota Engineering Standard - Sealing Foams for Interior Trim

TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
6.2.1 Flammability 6.2.1, Initial, Component	FMVSS 302 < 10 cm / min	EBRZT	Pass
6.3 Adhesive Peel Strength 6.3.2, Initial, 10 mins @ RT	ASTM D3330 7 N / 25 mm	19.4	Pass
6.3.2, Normal 24 hrs @ RT	7 N / 25 mm	21.5	Pass
6.3 Adhesive Shear Strength 6.3.3, Initial, 10 mins @ RT	ASTM D1002 100 kPa	99.3 Tear	Pass
6.3.3, Normal 24 hrs @ RT	100 kPa	107.0 Tear	Pass
6.3 Adhesive Durability, Peel Strength 6.3.4, Heat Aging, 240 hrs @ 80°C	ASTM D3330 7.0 N / 25 mm	28.9	Pass
6.3.5, Humidity Aging, 240 hrs @ 50°C / 95% RH	7.0 N / 25 mm	21.3	Pass
6.3.6, Thermal Cycling 3X 15.5 hrs @ 80°C 0.5 hrs @ RT 7.5 hrs @ -30°C 0.5 hrs @ RT 15.5 hrs @ 50°C / 95% RH 0.5 hrs @ RT 7.5 hrs @ -30°C 0.5 hrs @ RT	7.0 N / 25 mm	22.1	Pass
6.3.7, High Temp Bonding, 30 mins @ 80°C	3.0 N / 25 mm	11.3	Pass

CERTIFIED BY:
 Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
 This laboratory is not accredited for the calibrations or tests marked *.