



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **A5709A**
SUPPORT: **2 MIL PET**
SUBSTRATE: **SS**
CERT NO.: 230109 - 1111



TOYOTA TSK 6712G -OT
OEM Rev Date: Sep 05
Toyota Engineering Standard - Sealing Foams for Interior Trim

Tested in accordance with JDC protocols and provided as product information only. Actual product and application substrates would need to be tested for OEM certification.

TAPE REQUIREMENTS:

SECTION:	ASTM	Specification	Results	Status
6.3 Adhesive Peel Strength	ASTM D3330	7 N / 25 mm		
6.3.2, Initial, 10 mins @ RT			8.8	Pass
6.3.2, Normal 24 hrs @ RT			9.7	Pass
6.3 Adhesive Shear Strength	ASTM D1002	100 kPa		
6.3.3, Initial, 10 mins @ RT			282.7	Pass
6.3.3, Normal 24 hrs @ RT			346.2	Pass
6.3 Adhesive Durability, Peel Strength	ASTM D3330	7 N / 25 mm		
6.3.4, Heat Aging, 240 hrs @ 80°C			15.0	Pass
6.3.5, Humidity Aging, 240 hrs @ 50°C / 95% RH			7.7	Pass
6.3.6, Thermal Cycling 3X			9.0	Pass
15.5 hrs @ 80°C				
0.5 hrs @ RT				
7.5 hrs @ -30°C				
0.5 hrs @ RT				
15.5 hrs @ 50°C / 95% RH				
0.5 hrs @ RT				
7.5 hrs @ -30°C				
0.5 hrs @ RT				
6.3.7, High Temp Bonding, 30 mins @ 80°C			13.0	Pass
6.3.8 Creep		< 5 mm		
6.3.8.1, Peel Creep Test @ 90°, 24 hrs @ 80°C and .2 N (20 g) load			3.5	Pass
6.3.8.2, Shear Creep Test 180° 24 hrs @ 80°C and .5 N (50 g) load		> 1440 mins	> 1440	Pass
6.4 Smell	TSM 0505G	> 1.5 Rating		
6.4, Initial Smell, 1 hr @ 80°C, 30 mins @ RT			Rather Pleasant 1	Pass
6.4, After Aging Smell, 96 hrs @ 80°C, 30 mins @ RT, 1 hr @ 80°C, 30 mins @ RT			Neither Pleasant nor Unpleasant - 0	Pass

CERTIFIED BY:
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.