



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 0900X**
 SUPPORT: **FLOCK**
 SUBSTRATE: **FOIL**
 CERT NO.: **221222 - 0750**



VOLKSWAGEN AG PV 3015
 Test Method Rev Date: May 94
 Non-Metallic Materials for Interior Trim
 Velour
 Reference Spec : PV 50180

TAPE REQUIREMENTS:

SECTION: Fogging, Oil Bath	PV 3015*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
Sample 1, 16 hrs @ 100°C, 21°C Cooling, Post - 4 hrs @ RT (desiccator)		< / = 2 mg	0.30	Pass
Sample 2, 16 hrs @ 100°C, 21°C Cooling, Post - 4 hrs @ RT (desiccator)		< / = 2 mg	0.33	Pass
Sample 3, 16 hrs @ 100°C, 21°C Cooling, Post - 4 hrs @ RT (desiccator)		< / = 2 mg	0.63	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.