



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 0900X PET**  
 SUPPORT: **FLOCK**  
 SUBSTRATE: **FOIL**  
 CERT NO.: **221222 - 0750**



**VOLKSWAGEN AG PV 3015**  
 Test Method Rev Date: May 94  
 Non-Metallic Materials for Interior Trim  
 Velour  
 Reference Spec : PV 50180

**TAPE REQUIREMENTS:**

SECTION: **Fogging, Oil Bath**

PV 3015\*

Sample 1, 16 hrs @ 100°C, 21°C Cooling, Post - 4 hrs @ RT (desiccator)

**Specification**

**< / = 2 mg**

**Results**

0.38

**Status**

**Pass**

Sample 2, 16 hrs @ 100°C, 21°C Cooling, Post - 4 hrs @ RT (desiccator)

**< / = 2 mg**

0.47

**Pass**

Sample 3, 16 hrs @ 100°C, 21°C Cooling, Post - 4 hrs @ RT (desiccator)

**< / = 2 mg**

0.35

**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.