



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392 12 PT BD
SUPPORT: PEU FOAM
SUBSTRATE: ABS
CERT NO.: 230103 - 0827

CHRYSLER MS-AY-301-B1
OEM Rev Date : Apr 03
Cellular Polyurethane - Low Density
Cellular Polyurethane with Room Temp PSA
Type 1 - Table 2



TEST PARAMETERS:

Requirements for a Room Temp PSA

SECTION: 3.3.2 Adhesion Test

2.1, Adhesion Test, Initial, Room Temp

ASTM D903

Specification

274 N / m

Results

1419.7

Status

Pass

SECTION: 3.3.2 Adhesion Test

Adhesion Test, 2.2, Heat Aged, 168 hrs @ 60°C

ASTM D903

Specification

330 N / m

Results

2826.5

Status

Pass

SECTION: 3.3.2 Adhesion Test

2.3, Adhesion Test, After Thermo-Cycling

Cycles, 2x Table 2 70°C
24 hrs @ 70°C
24 hrs @ 38°C / 95% RH
24 hrs @ -30°C
Repeat twice then
168 hrs @ 70°C

Specification

No Loss of Adhesion or Detrimental Effect

Results

Good, Stable No Lifting

Status

Pass

SECTION: 3.3.2 Adhesion Test

2.4, Adhesion Test, Heat Resistance, 8 hrs @ 70°C

Specification

No Shrinkage, Loss of Adhesion or
Detrimental Effect

Results

Good, No Adhesion Loss or Lift

Status

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.