



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@everydennison.com
URL: tapes.everydennison.com

PRODUCT: FT 8392 12 PT BD
SUPPORT: PEU FOAM
SUBSTRATE: ABS
CERT NO.: 230103 - 0828

CHRYSLER MS-AY-301-B2
OEM Rev Date : Apr 03
Cellular Polyurethane - Low Density
Cellular Polyurethane with High Temp PSA
Type 2 - Table 3



TEST PARAMETERS:

Requirements for a Room Temp PSA

SECTION: 3.3.2 Adhesion Test	ASTM D903	Specification	Results	Status
2.1. Adhesion Test, Initial, Room Temp		274 N / m	1419.7	Pass

SECTION: 3.3.2 Adhesion Test	ASTM D903	Specification	Results	Status
Adhesion Test, 2.2, Heat Aged, 168 hrs @ 60°C		330 N / m	2826.5	Pass

SECTION: 3.3.2 Adhesion Test	<u>Specification</u>	<u>Results</u>	<u>Status</u>
2.3, Adhesion Test, After Thermo-Cycling Cycles, 2x Table 3 79°C 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -30°C Repeat twice then 168 hrs @ 79°C	No Loss of Adhesion or Detrimental Effect	Good, Stable No Lifting	Pass

SECTION: 3.3.2 Adhesion Test	Specification	Results	Status
2.4. Adhesion Test, Heat Resistance, 8 hrs @ 79°C	No Shrinkage, Loss of Adhesion or Detrimental Effect	Good, No Adhesion Loss or Lift	Pass

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.