



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FBA 8960  
SUPPORT: 2.5 MM EPDM FOAM  
SUBSTRATE: ABS  
CERT NO.: 240119 - 0646



### CHRYSLER MS-AY-430 B

OEM Rev Date: May 11

Die-Cut Ethylene Propylene Diene Monomer (EPDM) Closed Cell Rubber  
Type 2  
B - Cellular EPDM with PSA

#### TEST PARAMETERS:

##### SECTION: 5.0 Adhesion

Specification: **No Adhesion Loss or Separation**

Adhesion, Environment Cycling, Cycles (2X)

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

<u>Results</u>	<u>Status</u>
Good, Stable, no Lifting	Pass

##### SECTION: 5.0 Adhesion Test

ASTM D903-98 10

Specification: **274**

N / m

Adhesion Test, 20 mins @ RT

Results

1107.4

Status

Pass

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.