



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

PRODUCT: **FT 8327**
SUPPORT: **EPDM FOAM**
SUBSTRATE: **10% TALC PP**
CERT NO.: **221222 - 0832**



CHRYSLER MS-AY-430 C1

OEM Rev Date: May 11
Die-Cut Ethylene Propylene Diene Monomer (EPDM) Closed Cell Rubber
Type 1
C - Cellular EPDM with PSA and Polyester Film

TEST PARAMETERS:

SECTION: **5.0 Adhesion**

Specification: **No Adhesion Loss or Separation**

Adhesion, Environment Cycling, Cycles (2X)

72 hrs @ 70° C

24 hrs @ 38° C / 95% RH

72 hrs @ -40° C

Results

Good, Stable, no Lifting

Status

Pass

SECTION: **5.0 Adhesion Test**

ASTM D903

Specification: **274**

N / m

Results

446.6

Status

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.