



250 Chester Street

Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FM 2454**
 SUPPORT: **2 MIL ALUMINUM FOIL**
 SUBSTRATE: **GLASS**
 CERT NO.: **230103 - 0831**

CHRYSLER MS-AY-518-B2

OEM Rev Date: Oct 10

Ethylene Vinyl Acetate (EVA) - Cellular - Water and Dust Seals
B2 - Type 2 with High Temperature PSA (79°C)**TAPE REQUIREMENTS:****Table 2 Physical Properties of Adhesive Systems**

TEST:	1. Initial	<u>Specification</u>	<u>Results</u>	<u>Status</u>
	1, Initial, 20 mins @ Room Temp	274 N / m	1824.9	Pass

TEST:	2. Extended Term Heat Aging	<u>Specification</u>	<u>Results</u>	<u>Status</u>
	2, Extended Term Heat Aging, 168 hrs @ 70°C	330 N / m	1784.0	Pass

TEST:	3. Thermo Cycling 4.3.1	<u>Specification</u>	<u>Results</u>	<u>Status</u>
	3, Thermo Cycling 4.3.1 - Grade 2 High Temp 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C 2 Cycles then 168 hrs @ 79°C	No Shrink, Loss of Adhesion or Detrimental Effect	No Lifting, Shrink or Loss of Adhesion	Pass

TEST:	4. Short Term Heat Aging	ASTM D573 -08 *	<u>Specification</u>	<u>Results</u>	<u>Status</u>
	4, Short Term Heat Aging, 8 hrs @ 79°C		No Shrink, Loss of Adhesion or Detrimental Effect	No Lifting, Shrink or Loss of Adhesion	Pass

TEST:	8. Burn Rate	<u>Specification</u>	<u>Results</u>	<u>Status</u>
	8, Initial, Component	100 mm / min	< B 25	Pass

CERTIFIED BY:

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.