



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 1126 12 PT BD  
SUPPORT: NITRILE VINYL FOAM  
SUBSTRATE: E-COATED METAL  
CERT NO.: 230103 - 0837



### CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material  
Cellular PVN with PSA

#### TEST PARAMETERS:

SECTION:	Test Description	Shrink	ASTM D3575-08*	Substrate	Results	Status
SECTION: 2.1	Heat Aging Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C			Substrate ABS	Stable, Less than 5% Length and Width	Pass
	Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C			Substrate PP	Stable, Less than 5% Length and Width	Pass
	Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C			Substrate E-COATED METAL	Stable, Less than 5% Length and Width	Pass
SECTION: 2.2	Adhesion Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C			Substrate ABS	Results Good, Stable, no Lifting	Pass
	Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C			Substrate PP	Results Good, Stable, no Lifting	Pass
	Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C			Substrate E-COATED METAL	Results Good, Stable, no Lifting	Pass

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.