



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1158
SUPPORT: EPDM FOAM
SUBSTRATE: E-COATED METAL
CERT NO.: 230105 - 1158

CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
Cellular PVN with PSA



TEST PARAMETERS:

SECTION:	Test Description	Shrink	ASTM D3575-08*	Substrate	Results	Status
2.1	Heat Aging Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C			ABS	Stable, Less than 5% Length and Width	Pass
	Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C			PP	Stable, Less than 5% Length and Width	Pass
	Specification: < 5% 2.1, Heat Aging, 30 mins @ 100° C			E-COATED METAL	Stable, Less than 5% Length and Width	Pass
2.2	Adhesion Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C			ABS	Good, Stable, no Lifting	Pass
	Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C			PP	Good, Stable, no Lifting	Pass
	Specification: No Adhesion Loss or Delamination 2.2, Adhesion, Cycles (2X) 72 hrs @ 70° C 24 hrs @ 38° C / 95% RH 72 hrs @ -40° C			E-COATED METAL	Good, Stable, no Lifting	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.