



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **HPA 1905**
SUPPORT: **EPDM FOAM**
SUBSTRATE: **ABS**
CERT NO.: 230103 - 0838



CHRYSLER MS-AY-522 B TYPE 1

OEM Rev Date: Jul 06

Polyvinyl / Nitrile (PVN) Blend Semi-Open Cellular Material
Cellular PVN with PSA

TEST PARAMETERS:

SECTION:	TEST	Shrink	ASTM D3575-08*	Substrate	Results	Status
SECTION: 2.1	Heat Aging			Substrate		
Specification:	< 5%			ABS	Stable, Less than 5% Length and Width	Pass
2.1, Heat Aging, 30 mins @ 100° C						
Specification:	< 5%			Substrate		
2.1, Heat Aging, 30 mins @ 100° C				E-COATED METAL	Stable, Less than 5% Length and Width	Pass
Specification:	< 5%			Substrate		
2.1, Heat Aging, 30 mins @ 100° C				SS	Stable, Less than 5% Length and Width	Pass
SECTION: 2.2	Adhesion					
Specification:	No Adhesion Loss or Delamination					
2.2, Adhesion, Cycles (2X)				Substrate		
72 hrs @ 70° C				ABS		
24 hrs @ 38° C / 95% RH					Good, Stable, no Lifting	Pass
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination					
2.2, Adhesion, Cycles (2X)				Substrate		
72 hrs @ 70° C				E-COATED METAL		
24 hrs @ 38° C / 95% RH					Good, Stable, no Lifting	Pass
72 hrs @ -40° C						
Specification:	No Adhesion Loss or Delamination					
2.2, , Cycles (2X)				Substrate		
72 hrs @ 70° C				SS		
24 hrs @ 38° C / 95% RH					Good, Stable, no Lifting	Pass
72 hrs @ -40° C						

CERTIFIED BY:

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.